

the ink receiving layer is porous, apparent density thereof is 0.2 to 0.8 g/cm³ and heat conductivity of the ink receiving layer and the substrate is 0.1 to 0.25 W/mK, wherein center line average roughness of the ink receiving layer surface is [.20] 0.20 to 0.45 μm .

3. (Original): A recording material of claim 1, wherein the average pore diameter of the surface layer of the ink receiving layer is 0.05 to 1 μm .

4. (Previously Amended): A recording material of claim 1, wherein statical coefficient of friction observed between the ink receiving layer surface and a recording material back surface is 0.1 to 0.7, dynamical coefficient of friction observed between the ink receiving layer surface and the recording material back surface is 0.1 to 0.6 and the stiffness of the recording material in the longitudinal direction thereof is 40 to 300 cm³ when measured according to JIS P 8143.

5. (Previously Amended): A recording material of claim 1, wherein the average pore diameter of the surface layer of the ink receiving layer is 0.05 to 1 μm , statical coefficient of friction observed between the ink receiving layer surface and a recording material back surface is 0.1 to 0.7, dynamical coefficient of friction observed between the ink receiving layer surface and the recording material back surface is 0.1 to 0.6 and the stiffness of the recording material in the longitudinal direction thereof is 40 to 300 cm³ when measured according to JIS P 8143.

6. (Original): A recording material of claim 2, wherein the average pore diameter of the surface layer of the ink receiving layer is 0.05 to 1 μm .

7. (Previously Amended): A recording material of claim 2, wherein statical coefficient of friction observed between the ink receiving layer surface and a recording material back surface is 0.1 to 0.7, dynamical coefficient of friction observed between the ink receiving layer surface and the recording material back surface is 0.1 to 0.6 and the stiffness of the recording material in the longitudinal direction thereof is 40 to 300 cm³ when measured according to JIS P 8143.

8. (Previously Amended): A recording material of claim 2, wherein the average pore diameter of the surface layer of the ink receiving layer is 0.05 to 1 μm , statical coefficient of friction observed between the ink receiving layer surface and a recording material back surface is 0.1 to 0.7, dynamical coefficient of friction observed between the ink receiving layer surface and the recording material back surface is 0.1 to 0.6 and the stiffness of the recording material in the longitudinal direction thereof is 40 to 300 cm³ when measured according to JIS P 8143.

9. (Previously Amended): A recording material in which an ink receiving layer containing at least a resin and a pigment is provided on a substrate characterized in that the ink receiving layer is porous, apparent density thereof is 0.2 to 0.8 g/cm³ and center line average roughness of the ink receiving layer surface is 0.20 to 0.45 μm .


10. (Original): A recording material of claim 9, wherein the average pore diameter of the surface layer of the ink receiving layer is 0.05 to 1 μm .

11. (Previously Amended): A recording material of claim 9, wherein statical

coefficient of friction observed between the ink receiving layer surface and a recording material back surface is 0.1 to 0.7, dynamical coefficient of friction observed between the ink receiving layer surface and the recording material back surface is 0.1 to 0.6 and the stiffness of the recording material in the longitudinal direction thereof is 40 to 300 cm³ when measured according to JIS P 8143.

12. (Previously Amended): A recording material of claim 9, wherein the average pore diameter of the surface layer of the ink receiving layer is 0.05 to 1 μm , statical coefficient of friction observed between the ink receiving layer surface and a recording material back surface is 0.1 to 0.7, dynamical coefficient of friction observed between the ink receiving layer surface and the recording material back surface is 0.1 to 0.6 and the stiffness of the recording material in the longitudinal direction thereof is 40 to 300 cm³ when measured according to JIS P 8143.

Respectfully submitted,



Patrick D. McPherson
Reg. No. 46,255
Mark C. Comtois
Reg. No. 46,285
L. Lawton Rogers, III
Reg. No. 24,302
D. Joseph English
Reg. No. 42,514

DUANE MORRIS LLP
1667 K Street, N.W., Suite 700
Washington, D.C. 20006
Telephone: (202) 776-7800
Telecopier: (202) 776-7801

Dated: February 20, 2003